



Epoxy &  
Polyurethane  
Manufacturing and  
Research

## TECHNICAL BULLETIN

### KEMIKO® STONE TONE BUFF ON WAX Solvent Based

#### Description

KEMIKO® STONE TONE BUFF ON WAX - Solvent Based is especially formulated to produce a low sheen finish with high protection and durability. Designed for interior use over KEMIKO® STONE TONE STAIN, pigmented colored concrete, tile, brick, or any masonry surface.

#### Physical Characteristics

Dry Time	20 - 30 minutes
Coverage	250-350 ft <sup>2</sup> /gallon (will vary due to differences in porosity)
Thinning	Mineral spirits or paint thinner

#### Surface Preparation

Surface must be thoroughly cured and dry, free from all dark alkali, moisture spots, paint, wax, grease, and surface contaminant.

#### Application Methods

KEMIKO® STONE TONE BUFF ON WAX - Solvent Based may be applied by hand, it is highly recommended that the wax be applied using a heavy duty floor machine with three attachments; a stiff natural bristle brush (most critical), a medium bristle brush, and a buffing pad.

Since machine buffing is difficult near walls and corners, spread a smooth light coating of wax out from the walls (2-3 inches) and in the corners to allow for buffing radius of the floor machine. Put no more than ¼ cup of wax on the floor in the center of the first 3-4 foot square. It will appear wet and dull.

Immediately work the wax by spreading and burning it in with the natural stiff bristle attachment (this may take 4-5 minutes). Move to the next 3-4 foot quadrant and repeat the step only after the wax in the preceding area has turned to a light glare and the wax ridges have disappeared. Mineral spirits will soften any ridges or excess wax allowing it to be spread and worked in.

When you have completed the application phase, change to the medium bristle brush attachment and buff the entire floor including your original wall/corner application. After buffing, if greater protection is desired, repeat the first phase applying a thin second coat. Then rebuffer. If a slightly higher sheen is desired, buff with the soft pad. KEMIKO® STONE TONE BUFF ON WAX - solvent based is designed to be used with a floor buffing machine and special pad.

#### Clean-Up

Clean tools and equipment with paint thinner or mineral spirits.



Epoxy &  
Polyurethane  
Manufacturing and  
Research

## TECHNICAL BULLETIN

### KEMIKO® STONE TONE BUFF ON WAX Solvent Based

#### CAUTION

Keep away from heat and open flame. Avoid prolonged breathing of vapor or spray mist. Avoid prolonged or repeated contact with skin. Do not take internally. Do not transfer contents to bottles or other unlabeled containers. Keep closures tight and upright to prevent leakage. In case of spillage, absorb and dispose of in accordance with local applicable regulations.

#### First Aid

In case of skin contact, flush with plenty of water; for eyes, immediately flush with plenty of water for 15 minutes and get medical attention. If inhaled, remove to fresh air. If swallowed, **CALL A PHYSICIAN IMMEDIATELY. DO NOT** induce vomiting. Use with adequate ventilation. **KEEP OUT OF REACH OF CHILDREN. NON-PHOTOCHEMICALLY REACTIVE.**

Contact EPMAR for any additional application information.

#### Warranty

The following warranty is made in lieu of all other warranties, either expressed or implied. This product is manufactured of selected raw materials by skilled technicians. Neither seller nor manufacturer has any knowledge or control concerning the purchaser's use of this product and no warranty is made as to the results of any use. The only obligation of either seller or manufacturer shall be to replace any quantity of this product, which is proved to be defective. Any claim of defective product must be received in writing within one (1) year from date of shipment. Neither seller nor manufacturer assumes any liability for injury, loss, or damage resulting from use of this product.

**Service is part of our formula**

#### **Epmar Corporation**

13210 Barton Circle, Santa Fe Springs, CA 90605-3254  
Ph: 562.946.8781 / Fax: 562.944.9958  
[www.epmar.com](http://www.epmar.com)